Brandenburger


REINGO
ACEROS Y SUMINISTROS INDUSTRIALES
J. MIGUEL GONZALEZ
Leceaga, 7 lonja - 48002 BILBAO
Tel.: **94 427 70 93** - Móvil: **669 78 56 04** - Fax: **94 427 73 21**
reingosum@euskalnet.net • www.reingosum.com

Engineered Insulation Solutions

Excerpt from the product programme

	Temperature resistance in °C long-term	short-term	Compressive strength at 23 °C in N/mm² EN ISO 604	200 °C in N/mm² EN ISO 604	Coefficient of thermal conductivity in W/mK DIN 52 612	Option* High performance coating
Pressure-resistant Insulation Materials up to 300°C						
KV® 3	250	280	650	450	0,25	X
KV® 3*eco*	250	280	650	500	0,25	X
BRA-GLA® SI	280	350	450	200	0,22	X
BRA-GLA® 3	230	250	650	350	0,30	X
BRA-GLA® N	210	230	600	290	0,30	X
S 4000® HT	230	250	450	200	0,13	X
S 4000®	210	250	300	100	0,12	X
XGD® 60	210	250	610	300	0,30	X
XGD® 25	200	230	350	150	0,12	X
XGD® 16 New!	180	200	340	130	0,18	X
Pressure-resistant Insulation Materials exceeding 300°C						
BRA-BOARD® HT 175	1000	1100	34	30	0,22	
BRA-BOARD® HT 4	850	935	15	10	0,09	
BRA-BOARD® T	500	550	100	75	0,30	
GL®-P	500	800	330	240	0,31	
GL®-M	400	600	400	250	0,30	
Exterior Insulation Materials						
BRA-GLA® KA	450	500	7	4	0,05	X
BRA-FLEX®	280	300	-	-	0,06	
BRA-GLA® MP	270	280	9	5	0,09	
BRA-GLA® HC	230	250	3,1	2,8	0,08	
S 4000® A New!	230	250	120	14	0,08	X
XGD® 15 New!	200	220	250	80	0,12	X

* These products can be equipped with our FP-BRA-Coating which grants an effective protection against aggressive acting media e.g. hydraulic oil or steam.



Brandenburger

Development Production Service

Brandenburger special products

	Temperature resistance in °C		Compressive strength at 23 °C in N/mm² EN ISO 604	Compressive strength at 200 °C in N/mm² EN ISO 604	Coefficient of thermal conductivity in W/mK DIN 52 612
	long-term	short-term			
Slide Bearing Materials					
BL® 70	280	290	15	2	0,31
BL® 30 New!	230	250	300	110	0,45
Ablation Materials					
S 7000	230	3000	-	-	0,35
S 5000®	230	3000	200	90	0,35
S 2000®	200	3000	350	130	0,25
Compensation layers					
AE 2000 N	200	220	300	150	-
Mounting tools					
Mounting paste	300	1400	-	-	-
Ceramic non adhesive medium	300	1200	-	-	-

"simply better insulated"

REINGO
ACEROS Y SUMINISTROS INDUSTRIALES
J. MIGUEL GONZALEZ
Leceaga, 7 lonja - 48002 BILBAO
Tel.: **94 427 70 93** - Móvil: **669 78 56 04** - Fax: **94 427 73 21**
reingosum@euskalnet.net • www.reingosum.com